

|   |                           |                          |
|---|---------------------------|--------------------------|
| TRANSMITTAL LETTER TO UNITED STATES     |                           | Attorney's Docket Number |
| DESIGNATED/ELECTED OFFICE (DO/EO/US)    |                           | 07553.0018               |
| CONCERNING A FILING UNDER 35 U.S.C. 371 |                           | U.S. Application No.     |
|   |                           | 09/700785                |
| International Application. No.          | International Filing Date | Priority Date Claimed    |
| PCT/JP99/02578                          | 18 May 1999               | 22 May 1998              |

Title of Invention: ETCHING METHOD


Applicants For DO/EO/US: Youbun ITO; Masahiro YAMADA; Kouichiro INAZAWA

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. [X] This is a FIRST submission of items concerning a filing under 35 U.S.C. 371.
2. [ ] This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371.
3. [ ] This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).
4. [X] A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. [X] A copy of the International Application as filed (35 U.S.C. 371(c)(2))
  - a. [ ] is transmitted herewith (required only if not transmitted by the International Bureau).
  - b. [X] has been transmitted by the International Bureau.
  - c. [ ] is not required, as the application was filed in the United States Receiving Office (RO/US).
6. [X] A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7. [X] Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)).
  - a. [ ] are transmitted herewith (required only if not transmitted by the International Bureau).
  - b. [ ] have been transmitted by the International Bureau.
  - c. [ ] have not been made; however, the time limit for making such amendments has NOT expired.
  - d. [X] have not been made and will not be made.
8. [ ] A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. [ ] An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
10. [X] A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11. to 16. below concern other document(s) or information included:

11. [X] An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12. [ ] An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. [ ] A FIRST preliminary amendment.
14. [ ] A SECOND or SUBSEQUENT preliminary amendment.
15. [ ] A substitute specification.
16. [X] Other items or information:
  - a. [X] Cover page of WIPO Publication No. WO99/62111.
  - b. [ ] Copy of Notification of Missing Requirements.



U.S. APPLICATION NO. **097700785**INTERNATIONAL APPLICATION NO.  
PCT/JP99/02578ATTORNEY DOCKET NUMBER  
07553.0018

|  |              |              |                        |                  |
|--|--------------|--------------|------------------------|------------------|
| 17. [X] The following fees are submitted:  |              |              |                        | CALCULATIONS     |
| <b>Basic National Fee (37 CFR 1.492(a)(1)-(5)):</b>  |              |              |                        |                  |
| Search Report has been prepared by the EPO or JPO.....\$860.00   |              |              |                        |                  |
| International preliminary examination fee paid to<br>USPTO (37 CFR 1.482).....\$690.00   |              |              |                        |                  |
| No international preliminary examination fee paid to<br>USPTO (37 CFR 1.482) but international search fee<br>paid to USPTO (37 CFR 1.445(a)(2)).....\$760.00       |              |              |                        |                  |
| Neither international preliminary examination fee<br>(37 CFR 1.482) nor international search fee<br>(37 CFR 1.445(a)(2)) paid to USPTO.....\$1,000.00              |              |              |                        |                  |
| International preliminary examination fee paid to USPTO<br>(37 CFR 1.482) and all claims satisfied provisions<br>of PCT Article 33(1)-(4).....\$ 100.00            |              |              |                        |                  |
| <b>ENTER APPROPRIATE BASIC FEE AMOUNT =</b>  |              |              |                        | <b>\$860.00</b>  |
| Surcharge of \$130.00 for furnishing the oath or declaration later than<br>[ ] 20 [ ] 30 months from the earliest claimed priority date<br>(37 CFR 1.492(e)).      |              |              |                        | \$               |
| Claims   | Number Filed | Number Extra | Rate                   |                  |
| Total Claims   | 6 -20=       |              | X \$18.00              | \$               |
| Independent Claims   | 2 - 3=       |              | X \$80.00              | \$               |
| Multiple dependent claim(s) (if applicable)  |              |              | +\$270.00              | \$270.00         |
| <b>TOTAL OF ABOVE CALCULATIONS =</b>   |              |              |                        | <b>\$1130.00</b> |
| Reduction by 1/2 for filing by small entity, if applicable.  |              |              |                        | \$               |
| <b>SUBTOTAL =</b>  |              |              |                        | <b>\$1130.00</b> |
| Processing fee of \$130.00 for furnishing the English translation later<br>than [ ] 20 [ ] 30 months from the earliest claimed priority date<br>(37 CFR 1.492(f)). |              |              |                        | \$               |
| <b>TOTAL NATIONAL FEE =</b>  |              |              |                        | <b>\$1130.00</b> |
| Fee for recording the enclosed assignment (37 CFR 1.21(h)). The<br>assignment must be accompanied by an appropriate cover sheet<br>(37 CFR 3.28, 3.31).            |              |              |                        | \$               |
|  |              |              | \$40.00 per property + | \$               |
| <b>TOTAL FEES ENCLOSED =</b>   |              |              |                        | <b>\$1130.00</b> |
| Amount to be<br>refunded   |              |              |                        | \$               |
| charged  |              |              |                        | \$               |

a. [X] A check in the amount of **\$ 1130.00** to cover the above fees is enclosed.b. [ ] Please charge my Deposit Account No. \_\_\_\_\_ in the amount of  
\$ \_\_\_\_\_

to cover the above fees. A duplicate copy of this sheet is enclosed.

c. [X] The Commissioner is hereby authorized to charge any additional fees  
which may be required, or credit any overpayment to Deposit Account  
No. 06-0916. A duplicate copy of this sheet is enclosed.The Commissioner is hereby authorized to charge any other fees due under 37 C.F.R. \$1.16  
or \$1.17 during the pendency of this application to our Deposit Account No. 06-0916.

SEND ALL CORRESPONDENCE TO:  
 Finnegan, Henderson, Farabow  
 Garrett & Dunner, L.L.P.  
 1300 I Street, N.W.  
 Washington, D.C. 20005-3315  
 DWH/FPD/peg

*David W. Hill*  
 David W. Hill  
 Reg. No. 28,220

Submitted: November 20, 2000

## SPECIFICATION

### ETCHING METHOD

### TECHNICAL FIELD

The present invention relates to an etching method that may be adopted in a process for manufacturing a semiconductor device.

### BACKGROUND ART

To keep pace with the great improvements made with respect to the degree of integration of semiconductor devices in recent years, miniaturization of various elements formed on semiconductor substrates has become one of the crucial technical requirements. In order to meet this requirement, the distances between the individual gates (electrodes) formed on a semiconductor substrate must be reduced, and if contact holes are formed between the gates, the contact holes, too, must be miniaturized. However, as the distances between the gates become increasing small, the difficulty in forming ever smaller contact holes at accurate positions increases, due to the limits of the alignment performance of the stepper and the like. Accordingly, a self-aligning contact technology, whereby self-aligned contact holes are formed within the minute space between individual gates by forming a protective film (base) constituted of, for instance, an  $\text{SiN}_x$  film at the surfaces of the gates and thereby preventing the gates from becoming etched during the contact hole formation, has been proposed of late. It is to be noted that  $\text{SiN}_x$  as referred to in this specification may indicate a state in which  $\text{SiN}$  and  $\text{Si}_3\text{N}_4$  are mixed as well as  $\text{SiN}$  or  $\text{Si}_3\text{N}_4$  itself.

A mixed gas containing, for instance,  $\text{C}_4\text{F}_8$  and  $\text{CO}$  is often used as the processing gas when forming contact holes at an  $\text{SiO}_2$  film (insulating film) covering the gates formed on a semiconductor

substrate by employing the self-aligning contact technology described above, so that the selection ratio of the  $\text{SiO}_2$  film layer relative to the  $\text{SiN}_x$  film layer is improved. Namely, by using such a processing gas in which  $\text{C}_4\text{F}_8$  constituting the processing gas contains a relatively large number of carbon atoms compared to  $\text{CF}_4$  or  $\text{C}_2\text{F}_6$  used in the prior art, a carbon film to constitute a protective film can be formed with ease at the inner wall surface of the contact holes. In addition, since CO is added in the processing gas, the formation of the carbon film is further facilitated. As a result, fluorine radicals constituting the etching ions do not readily come in contact with the  $\text{SiN}_x$  film layer covered by the carbon film, thereby achieving an improvement in the selection ratio of the  $\text{SiO}_2$  film layer relative to the  $\text{SiN}_x$  film layer.

However, while the selection ratio of the  $\text{SiO}_2$  film layer relative to the  $\text{SiN}_x$  film layer is improved due to the presence of the carbon film formed at the inner wall surface of the contact holes by forming the contact holes using a mixed gas containing  $\text{C}_4\text{F}_8$  and CO as described above, carbon becomes accumulated also at the bottoms of the contact holes. This results in the carbon accumulated at the bottoms of the contact holes preventing the fluorine radicals from reaching the bottoms with ease. Consequently, it becomes difficult to mill contact holes having a depth larger than a specific measurement, to lead to a reduction in the penetration and an etching stop.

In addition, while it has become one of the technological requirements in recent years to form contact holes achieving a high aspect ratio in extremely small spaces between gates, the structure of such deep contact holes makes it difficult for fluorine radicals to reach the bottoms of the contact holes. As a result, if the contact holes are formed by using the mixed gas containing  $\text{C}_4\text{F}_8$  and CO as described above, the accumulation of carbon at the bottoms of the contact holes and the reduction in the quantity of fluorine radicals

entering the contact holes further reduce the penetration and increases the occurrence of etching stop.

Furthermore, if contact holes are formed through a process in which carbon is accumulated readily at the bottoms of the contact holes as in the etching method in the prior art described above, it is necessary to perform over-etching on the semiconductor substrate in consideration of carbon which accumulates at the bottoms of the contact holes. However, if such an over-etching process is performed on the semiconductor substrate, the insulating film layer and the  $\text{SiN}_x$  film layer, which are respectively provided to cover and protect the gates are also etched, to result in the insulating film layer and the gates themselves becoming exposed inside the contact holes.

Consequently, problems such as defective insulation and shorting of the gates, other wiring or electrodes may occur to lower the yield. In particular, the shoulder (corners) of the  $\text{SiN}_x$  film layer, which often distend into the contact holes, tend to become etched very readily, and thus, if over-etching process is performed on the semiconductor substrate as described above, the worst damage is likely to occur at the corners. For this reason, the etching process can only be performed to an extent to which the shoulder of the  $\text{SiN}_x$  film layer do not become damaged in the etching method in the prior art, which makes it extremely difficult to form contact holes achieving a high aspect ratio.

A first object of the present invention, which has been completed by addressing the problems of the prior art discussed above, is to provide a new and improved etching method which achieves an improvement in the selection ratio of the  $\text{SiO}_2$  film layer relative to the  $\text{SiN}_x$  film layer by forming a carbon film (protective film) at the shoulder of the  $\text{SiN}_x$  film layer exposed inside the contact holes and makes it possible to form contact holes achieving a high aspect

ratio by minimizing the accumulation of carbon at the contact hole bottoms.

A second object of the present invention is to provide a new and improved etching method that eliminates excessive etching which may cause damage to the shoulder of the  $\text{SiN}_x$  film and achieves an improvement in yield by preventing defective insulation at the gates and the occurrence of dielectric breakdown.

### DISCLOSURE OF THE INVENTION

In order to achieve the objects described above, in a first aspect of the present invention, an etching method for plasma-etching an  $\text{SiO}_2$  film layer covering an  $\text{SiN}_x$  film layer formed at a workpiece placed within an air-tight processing chamber by raising to plasma a processing gas induced into the processing chamber, which is characterized in that the processing gas is a mixed gas containing, at least,  $\text{C}_4\text{F}_8$  and  $\text{CH}_2\text{F}_2$ , is provided.

In this etching method in which  $\text{CH}_2\text{F}_2$  is used in the processing gas instead of  $\text{CO}$ , fluorine radicals can be generated from  $\text{CH}_2\text{F}_2$  as well as from  $\text{C}_4\text{F}_8$  to increase the quantity of fluorine radicals generated during the process. As a result, even when forming contact holes with a high aspect ratio, fluorine radicals can reach the bottoms of the contact holes with a high degree of reliability to make it possible to etch the bottoms while removing carbon accumulated at the bottoms of the contact holes, thereby facilitating the formation of contact holes with a specific depth.

In addition, since the bottoms of the contact holes can be etched with a high degree of reliability, it is not necessary to over-etch the workpiece and thus, damage to the  $\text{SiN}_x$  film layer exposed inside the contact holes and, in particular, damage to the shoulder of the  $\text{SiN}_x$  film layer can be prevented. As a result, since the insulating film layer

covering the gates protected by  $\text{SiN}_x$  film layer or the gates themselves are not exposed inside the contact holes, defective insulation at the gates and the occurrence of dielectric breakdown are prevented to achieve an improvement the yield. Furthermore, since the bottoms of the contact holes can be etched while sustaining a specific etching rate, the length of time required to perform the etching process can be reduced to achieve an improvement in throughput, as well.

Since  $\text{CH}_2\text{F}_2$  constituting the processing gas contains carbon atoms, a carbon film to constitute a protective film can be formed at the inner wall surface of the contact holes with a high degree of reliability as in an etching method which utilizes a processing gas containing CO. Consequently, the inner wall surface of the contact holes are not etched readily, to prevent formation of contact holes with a bowed shape. Moreover, with the  $\text{SiN}_x$  film layer exposed inside the contact holes and, in particular, the shoulder of the  $\text{SiN}_x$  film layer, covered with the carbon film, the shoulder do not become etched and, therefore, damage to the shoulder is prevented. In addition, since fluorine radicals reach the bottoms of the contact holes with a high degree of reliability even though the processing is performed on the workpiece in a carbon-rich atmosphere in this manner, carbon does not accumulate at the bottoms of the contact holes.

In a second aspect of the present invention, an etching method for plasma-etching an  $\text{SiO}_2$  film layer covering an  $\text{SiN}_x$  film layer formed at a workpiece placed inside an air-tight processing chamber by raising to plasma a processing gas induced into the processing chamber, which includes a first step in which the  $\text{SiO}_2$  film layer is etched by using a mixed gas containing at least  $\text{C}_4\text{F}_8$  and CO as the processing gas and a second step in which the  $\text{SiO}_2$  film layer is etched by using another mixed gas containing at least  $\text{C}_4\text{F}_8$  and  $\text{CH}_2\text{F}_2$

as the processing gas before or after the  $\text{SiN}_x$  film layer becomes exposed, e.g., immediately before or immediately after the  $\text{SiN}_x$  film layer becomes exposed, is provided.

In this etching method, in which the etching process is performed by using a mixed gas containing, at least,  $\text{C}_4\text{F}_8$  and  $\text{CO}$ , the workpiece can be etched as fast as in the etching method in the prior art described earlier in a carbon-rich atmosphere. As a result, a carbon film is formed at the inner wall surface of the contact holes with ease and the etching process can be completed quickly without bowing the shape of the etched contact holes.

In addition, since the etching process is implemented by switching to another mixed gas containing at least  $\text{C}_4\text{F}_8$  and  $\text{CH}_2\text{F}_2$  before or after the  $\text{SiN}_x$  film layer becomes exposed, the workpiece can be processed in a carbon-rich and radical-rich atmosphere. Thus, the carbon accumulated at the bottoms of the contact holes can be removed to achieve reliable etching at the bottoms, and with the occurrence of an etching stop prevented, an improvement in the penetration is achieved. Furthermore, since the use of such a processing gas makes it possible to prevent accumulation of carbon at the bottoms of the contact holes while depositing a carbon film at the shoulder of the  $\text{SiN}_x$  film layer, contact holes achieving a specific shape can be formed.

By setting the flow rate ratio ( $\text{CH}_2\text{F}_2 / \text{C}_4\text{F}_8$ ) of  $\text{C}_4\text{F}_8$  and  $\text{CH}_2\text{F}_2$  in the mixed gas containing at least  $\text{C}_4\text{F}_8$  and  $\text{CH}_2\text{F}_2$  to a value which is essentially within a range of  $0.4 \leq (\text{CH}_2\text{F}_2 / \text{C}_4\text{F}_8) \leq 1.0$  by setting the partial pressure corresponding to  $\text{C}_4\text{F}_8$  relative to the entire pressure of the mixed gas containing at least  $\text{C}_4\text{F}_8$  and  $\text{CH}_2\text{F}_2$  at a value which is essentially equal to or higher than 0.4 (mTorr) or equal to or lower than 0.8 (mTorr), the selection ratio of the  $\text{SiO}_2$  film layer relative to the  $\text{SiN}_x$  film layer can be further improved.



Moreover, by setting the density of the plasma excited inside the processing chamber at a value which is essentially equal to or higher than  $1.5 \times 10^{10}$  (number of ions /  $\text{cm}^3$ ) equal to or lower than  $1.2 \times 10^{11}$  (number of ions /  $\text{cm}^3$ ) or by placing the workpiece on the mounting surface of a suceptor provided inside the processing chamber and setting the temperature of the susceptor mounting surface at a value which is essentially equal to or higher than  $20^\circ\text{C}$  or higher and equal to or lower than the heat resistance temperature of the photoresist layer constituting the mask pattern of the the  $\text{SiO}_2$  film layer, the selection ratio of the  $\text{SiO}_2$  film layer relative to the  $\text{SiN}_x$  film layer can be further improved.

In addition, by adding an inert gas into the mixed gas containing at least  $\text{C}_4\text{F}_8$  and  $\text{CH}_2\text{F}_2$  or adding an inert gas into the mixed gas containing at least  $\text{C}_4\text{F}_8$  and  $\text{CO}$ , the various processing conditions such as the etching rate can be easily adjusted.

### **BRIEF DESCRIPTION OF THE DRAWINGS**

FIG. 1 is a schematic sectional view of an etching apparatus that may adopt the present invention;

FIG. 2 is a schematic sectional view illustrating a semiconductor wafer to be processed on the etching apparatus shown in FIG. 1;

FIG. 3 is a schematic sectional view of a semiconductor wafer having undergone an etching process in an example of implementation of the present invention;

FIG. 4 is a schematic sectional view of a semiconductor wafer having undergone an etching process in an example of implementation of the present invention;

FIG. 5 is a schematic sectional view of a semiconductor wafer having undergone an etching process in an example of implementation of the present invention;

FIG. 6 is a schematic sectional view of a semiconductor wafer having undergone an etching process in an example of implementation of the present invention;

FIG. 7 is a schematic sectional view of a semiconductor wafer having undergone an etching process in an example of implementation of the present invention;

FIG. 8 schematically illustrates the relationship between the flow rate ratio of the processing gas and the selection ratio of the  $\text{SiO}_2$  film at the semiconductor wafer;

FIG. 9 is a schematic sectional view of a semiconductor wafer having undergone an etching process in an example of implementation of the present invention;

FIG. 10 is a schematic sectional view of a semiconductor wafer having undergone an etching process in an example of implementation of the present invention;

FIG. 11 is a schematic sectional view of a semiconductor wafer having undergone an etching process in an example of implementation of the present invention;

FIG. 12 is a schematic sectional view of a semiconductor wafer having undergone an etching process in an example of implementation of the present invention;

FIG. 13 is a schematic sectional view of a semiconductor wafer having undergone an etching process in an example of implementation of the present invention;

FIG. 14 is a schematic sectional view of a semiconductor wafer having undergone an etching process in an example of implementation of the present invention; and

FIG. 15 is a schematic sectional view of a semiconductor wafer having been processed in an etching method in the prior art.

## THE BEST MODE FOR CARRYING OUT THE INVENTION

The following is a detailed explanation of an embodiment of the etching method according to the present invention, given in reference to the attached drawings.

### (1) Structure of etching apparatus

First, in reference to FIG. 1, an etching apparatus 100 that may adopt the etching method in the embodiment is explained.

Inside a processing container 102 of the etching apparatus 100 in the figure, a processing chamber 104 is formed, and inside the processing chamber 104, a lower electrode 106 constituting a susceptor capable of moving up and down freely is provided. On top of the lower electrode 106, an electrostatic chuck 110 connected to a high-voltage DC source 108 is provided, and a workpiece such as a semiconductor wafer (hereafter referred to as a "wafer") W is placed on the upper surface of the electrostatic chuck 110. In addition, a focus ring 112 achieving an insulating property is provided around the wafer W placed on the lower electrode 106. In addition, a conductive baffle plate 114 having numerous through holes 114a is provided via an insulator 107 around the lower electrode 106. The baffle plate 114 is electrically continuous with the grounded processing container 102 via, for instance, a stainless bellows 109. A high-frequency source 120 that outputs plasma-generating high frequency power is connected to the lower electrode 106 via a matcher 118.

At the ceiling of the processing chamber 104 facing opposite the mounting surface of the lower electrode 106, an upper electrode 122 having numerous gas outlet holes 122a is provided, and in the example illustrated in the figure, the upper electrode 122 constitutes part of the processing container 102. A gas supply pipe 124 is connected to the gas outlet holes 122a, and in the example shown in the figure, first ~ third branch pipes 126, 128 and 130 are connected

to the gas supply pipe 124. A gas supply source 136 that supplies  $C_4F_8$  is connected to the first branch pipe 126 via an open / close valve 132 and a flow-regulating valve 134. A gas supply source 142 that supplies  $CH_2F_2$  in the embodiment is connected to the second branch pipe 128 via an open / close valve 138 and a flow-regulating valve 140. A gas supply source 148 that supplies Ar is connected to the third branch pipe 130 via an open / close valve 144 and a flow-regulating valve 146. It is to be noted that the structure adopted to supply these individual processing gases is to be detailed later. The inert gas added into the processing gas is not limited to Ar in the example above and any inert gas such as Kr may be used instead, as long as it can be utilized to adjust the plasma excited inside the processing chamber 104. In addition, various types of gases such as  $O_2$ ,  $N_2$ , CO and  $CO_2$  may be added in the processing gas.

Furthermore, near the bottom of the processing container 102, a discharge pipe 150 which communicates with a vacuum drawing mechanism (not shown) is connected, and through the function of the vacuum drawing mechanism, the atmosphere inside the processing chamber 104 is sustained at a specific reduced pressure. Also, outside the processing chamber 104, a magnet 152 is provided so as to enclose the outer sidewalls of the processing container 102, and the magnet 152 forms the rotating magnetic field in the plasma area located between the upper electrode 122 and the lower electrode 106.

## (2) Structure of wafer

Next, in reference to FIG. 2, the structure of the wafer W to undergo the etching process in the etching apparatus described above is explained.

Gates 202 are formed on an Si (silicon) substrate 200 constituting the wafer W, with an insulating film layer 204 formed to cover the gates 202. In addition, an  $SiN_x$  film layer 206 is formed so as

to cover the surface of the insulating film layer 204. The  $\text{SiN}_x$  film layer 206 prevents the gates 202 from becoming etched during the formation of contact holes 210 which is to be detailed later and enables formation of a self-aligned contact hole 210 between the gates 202. In addition, a silicon oxide film constituting an insulating film layer, e.g., an  $\text{SiO}_2$  film layer 208 is formed over the  $\text{SiN}_x$  film layer 206. It is to be noted that the insulating film layer 204 and the  $\text{SiO}_2$  film 208 may be constituted of BPSG (silicate glass constituted of boron and phosphorus), PSG (silicate glass constituted of phosphorus), TEOS (tetra-ethoxy ortho-silane), Th-OX (thermal oxide) or SOG (spin glass). In addition, a photoresist layer 212 to constitute a mask pattern for the contact hole 210 is formed over the  $\text{SiO}_2$  film layer 208.

### (3) Contact hole formation process

Next, in reference to FIGS. 1 and 2, the process through which the contact hole 210 is formed between the gates 202 at the wafer W described above is explained.

First, the temperature of the mounting surface of the lower electrode 106 is adjusted to a level which is essentially equal to or higher than  $20^\circ\text{C}$  and equal to or lower than the heat resistance temperature of the photoresist layer 212, i.e., the temperature at which the photoresist layer 212 melts and, more desirably, within a range of  $20^\circ\text{C} \sim 60^\circ\text{C}$ , e.g., at  $40^\circ\text{C}$ , and then the wafer W is placed on the mounting surface.

Next, the processing gas in the embodiment, i.e., the mixed gas containing  $\text{C}_4\text{F}_8$ ,  $\text{CH}_2\text{F}_2$  and Ar is induced into the processing chamber 104. During this process, the flow rates of  $\text{C}_4\text{F}_8$ ,  $\text{CH}_2\text{F}_2$  and Ar are respectively adjusted at the corresponding regulating valves 134, 140 and 146. The flow rate of  $\text{C}_4\text{F}_8$  is set at a level which is essentially within the range of 5 (sccm)  $\sim$  15 (sccm) and more preferably within

the range of 6 (sccm) ~ 8 (sccm) in the embodiment. The flow rate of  $\text{CH}_2\text{F}_2$  is set at a level which is essentially within the range of 2 (sccm) ~ 10 (sccm) and more preferably within the range of 3 (sccm) ~ 5 (sccm). In addition, the flow rate of Ar is set at a level which is essentially within the range of 400 (sccm) ~ 600 (sccm) and more preferably at 500 (sccm). At the same time, the flow rates of the individual processing gases should be adjusted as appropriate so as to set the flow rate ratio ( $\text{CH}_2\text{F}_2 / \text{C}_4\text{F}_8$ ) of  $\text{C}_4\text{F}_8$  and  $\text{CH}_2\text{F}_2$  essentially in a range of 0.4 ~ 1.0, and more preferably, within the range of 0.53 ~ 0.8 and even more desirably within the range of 0.55 ~ 0.7.

Concurrently while the processing gas is being induced into the processing chamber 104, the vacuum drawing is implemented inside the processing chamber 104. At this time, the pressure atmosphere in the processing chamber 104 should be set essentially within the range of 30 (mTorr) ~ 70 (mTorr), and more desirably within the range of 35 (mTorr) ~ 55 (mTorr). At the same time, the pressure atmosphere in the processing chamber 104 should be adjusted as appropriate so as to set the partial pressure corresponding to  $\text{C}_4\text{F}_8$  relative to the entire pressure of the mixed gas containing  $\text{C}_4\text{F}_8$ ,  $\text{CH}_2\text{F}_2$  and Ar is within a range of 0.4 (mTorr) ~ 0.8 (mTorr).

Then, a rotating magnetic field is formed in the plasma area inside the processing chamber 104 by rotating the magnet 152. Then, a specific level of high-frequency power is applied to the lower electrode 106 to excite plasma inside the processing chamber 104. During this process, the high-frequency power should be adjusted so as to set the density of plasma excited inside the processing chamber 104 essentially within the range of  $1.5 \times 10^{10}$  (number of ions / cubic cm) ~  $1.2 \times 10^{11}$  (number of ions /  $\text{cm}^3$ ). In other words, in the embodiment, high-frequency power achieving a frequency of 13.56 (MHz) and a power level of 1400 (W) ~ 2000 (W) and, more preferably,

a power level of 1500 (W), for instance, is applied to the lower electrode 106. As a result, a glow discharge occurs between the upper electrode 122 and the lower electrode 106 to dissociate the processing gas in the embodiment having been induced into the processing chamber 104, thereby generating high-density plasma. Then, a specific type of etching process is performed on the wafer W with the plasma thus generated.

During this process, since the mixed gas comprising  $C_4F_8$ ,  $CH_2F_2$  and Ar is utilized as the processing gas in the embodiment, a carbon-rich atmosphere can be created from  $C_4F_8$  and  $CH_2F_2$  without having to add CO in the processing gas as necessary in the etching method in the prior art explained earlier. As a result, a carbon film can be formed with ease at the exposed surfaces of the  $SiN_x$  film layer 206, the  $SiO_2$  film layer 208 and the photoresist layer 212 constituting the inner side wall surface of the contact hole 210. Thus, since the inner side wall surface of the contact hole 210 does not become etched readily, the contact hole is not formed in a bowed shape.

In addition since the carbon layer covers the surface of the  $SiN_x$  film layer 206, and in particular, a shoulder 207 of the  $SiN_x$  film layer 206, fluorine radicals generated from  $C_4F_8$  and  $CH_2F_2$  are prevented from readily reaching the shoulder 207 which would be readily etched to prevent damage to the shoulder 207 of the  $SiN_x$  film layer 206. As a result, the selection ratio of the  $SiN_x$  film layer 206 and the  $SiO_2$  film layer 208 improves and the insulating film layer 204 and the gates 202 protected by the  $SiN_x$  film layer 206 do not become damaged, thereby preventing insulation defects at the gates and the occurrence of dielectric breakdown and achieving an improvement in yield.

By using  $CH_2F_2$  in the processing gas as in the embodiment instead of CO, fluorine radicals to constitute the etchant seed are also generated from  $CH_2F_2$  as well as from  $C_4F_8$ , to increase the quantity of

fluorine radicals contained in the plasma. Consequently, fluorine radicals can reach in a reliable manner the bottom of the contact holes 210 with a high aspect ratio formed in the extremely small space between the gates 202, to make it possible to remove carbon accumulated at the bottom with ease and to etch the bottom at a constant etching rate without reducing the penetration or causing an etching stop. Furthermore, since Ar is added into the processing gas, the density and the like of the plasma generated inside the processing chamber 104 can be adjusted as necessary.

In the embodiment which assumes the structure described above and utilizes the mixed gas constituted of  $C_4F_8$ ,  $CH_2F_2$  and Ar as the processing gas, a carbon-rich atmosphere is created as in an etching method which utilizes a processing gas containing CO, and a large quantity of fluorine radicals can be generated unlike in the etching method which utilizes a processing gas containing CO. As a result, the carbon film is formed at the inner side wall surface of the contact hole 210 alone and the accumulation of carbon at the bottom of the contact hole 210 is prevented, so that an insulation defect at the gates 202 and the occurrence of dielectric breakdown are prevented and the penetration of the contact hole 210 is improved even when the contact hole 210 formed in the extremely small space between the gates 202 has a high aspect ratio.

### **Examples of Implementation**

Next, specific examples in which the etching method according to the present invention is implemented are explained. It is to be noted that since contact holes 210 are formed between gates 202 formed at the wafer W by using the mixed gas containing  $C_4F_8$ ,  $CH_2F_2$  and Ar in the etching apparatus 100 in the embodiment explained above and by varying specific conditions such as the flow rates of the



processing gases, the pressure of the atmosphere in the processing chamber 104, the level of the high-frequency power applied to the lower electrode 106 and the temperature of the mounting surface of the lower electrode 106, the same reference numbers are assigned to components achieving roughly identical functions and structural features to those in the etching apparatus 100 and the wafer W explained earlier to preclude the necessity for repeated explanation thereof.

(A) Change in  $\text{CH}_2\text{F}_2$  flow rate

First, individual examples of implementation achieved by varying the flow rate of  $\text{CH}_2\text{F}_2$  are listed in the following table. It is to be noted that the etching process was performed in the individual implementation examples with the pressure of the atmosphere inside the processing chamber 104 set at 50 (mTorr), the temperature at the upper electrode 122 and the inner wall surfaces of the processing chamber 104 set at 60°C and the temperature of the lower electrode 110 set at 40 °C. In addition, high-frequency power achieving a frequency of 13.56 (MHz) and a power level of 1600 (W) was applied to the lower electrode 106. Wafers W having a 200mm diameter were used. The process was implemented in an etching apparatus 100 having a processing chamber 102 with a 38 (l) capacity.

In addition, the uniformity within the work surface of the wafer W (hereafter referred to as the "surface uniformity") and the selection ratio of the  $\text{SiO}_2$  film layer 208 relative to the  $\text{SiN}_x$  film layer 206 were ascertained for each implementation example, with the resulting cross sectional shape (etching shape) achieved in the wafer W illustrated in the corresponding figure. It is to be noted that the surface uniformity indicates by what percentages the etching rates at the center and at an edge deviate from the average etching rate calculated by averaging the etching rates at the center and the edge of the wafer W (referred to

as the "average etching rate" in the table), and the larger numerical value (absolute value) the degree of surface uniformity is not good and the smaller numerical value (absolute value) the degree of surface uniformity is good. In addition, the selection ratio of the  $\text{SiO}_2$  film layer 208 relative to the  $\text{SiN}_x$  film layer 206 (referred to as the " $\text{SiO}_2$  /  $\text{SiN}_x$  selection ratio" in the table) is represented by the average of values indicating  $(\text{SiO}_2 \text{ film layer etching rate}) / (\text{SiN}_x \text{ film layer etching rate})$  ratios at the center and an edge of the wafer W in a state in which the  $\text{SiN}_x$  film layer 206 is exposed with the etching process performed on the  $\text{SiO}_2$  film layer 208 at an advanced stage, as illustrated in FIG. 2.

Table 1

| Implementation example | Processing gas flow rates (sccm) |                                |     | Wafer surface uniformity (±%) | SiO <sub>2</sub> film layer average etching rate (lambda/min) | SiO <sub>2</sub> / SiN <sub>x</sub> selection ratio | Contact hole cross sectional shape |
|------------------------|----------------------------------|--------------------------------|-----|-------------------------------|---|---|------------------------------------|
|                        | C <sub>4</sub> F <sub>8</sub>    | CH <sub>2</sub> F <sub>2</sub> | Ar  |                               |   |   |                                    |
| 1                      | 7                                | 0                              | 500 | 1.2                           | 4250  | 15.6  | FIG. 3                             |
| 2                      | 7                                | 3                              | 500 | 1.2                           | 4050  | 18.6  | FIG. 4                             |
| 3                      | 7                                | 4                              | 500 | 1.2                           | 4050  | 34.4  | FIG. 5                             |
| 4                      | 7                                | 5                              | 500 | 5.0                           | 4000  | 24.8  | FIG. 6                             |
| 5                      | 7                                | 7                              | 500 | 5.1                           | 3900  | 25.5  | FIG. 7                             |

As indicated in the table above, by adjusting the flow rate of  $\text{CH}_2\text{F}_2$  to a value of approximately 4 (sccm), it can be assured that contact holes 210 achieving a specific shape can be formed without etching the shoulder 207 of the  $\text{SiN}_x$  film layer 206 exposed in the contact holes 210.

In addition, with the flow rate of  $\text{CH}_2\text{F}_2$  set at 4 (sccm), contact holes 210 achieving a specific shape were formed both at the center and at the edge of the wafer W as illustrated in FIG. 5. Namely, the shoulder 207 of the  $\text{SiN}_x$  film layer 206 were not etched and no carbon accumulated at the bottoms of the contact holes 210 either at the center or at the edge of the wafer W. By setting the flow rate of  $\text{CH}_2\text{F}_2$  at 3 (sccm) or 5 (sccm), too, contact holes each achieving a specific shape were formed as shown in FIGS. 4 and 6, as at the flow rate of 4 (sccm). However, when the flow rate of  $\text{CH}_2\text{F}_2$  was set at 0 (sccm) or 7 (sccm), the shoulder 207 of the  $\text{SiN}_x$  film layer 206 became etched, as shown in FIGS. 3 and 7 and, at the same time, carbon accumulated at the bottoms of the contact holes 210.

The results discussed above indicate that by setting the flow rate of  $\text{CH}_2\text{F}_2$  added in the mixed gas also containing  $\text{CH}_4\text{F}_8$  and Ar within the range of 3 (sccm) ~ 5 (sccm) when performing an etching process on the wafer W on the etching apparatus 100 under the various conditions outlined earlier, contact holes 210 achieving a specific shape can be formed over the entire surface of the wafer W. However, since the results given above were achieved by performing an etching process on the etching apparatus 100 as described above, it may not be possible to formed contact holes 210 achieving the specific shape at the same gas flow rate on another processing apparatus due to the difference in the capacity of the processing chamber and the like. Accordingly, by adjusting the flow rates of the individual processing gases in conformance to the flow rate ratio

( $\text{CH}_2\text{F}_2$  /  $\text{C}_4\text{F}_8$ ) of  $\text{C}_4\text{F}_8$  and  $\text{CH}_2\text{F}_2$  constituting the processing gas, contact holes 210 achieving a specific shape can be formed at all times without being affected by structural differences among etching apparatuses.

Now, in reference to FIG. 8, the relationship between the flow rate ratio ( $\text{CH}_2\text{F}_2$  /  $\text{C}_4\text{F}_8$ ) of  $\text{C}_4\text{F}_8$  and  $\text{CH}_2\text{F}_2$  and the selection ratio of the  $\text{SiO}_2$  film layer 208 relative to the  $\text{SiN}_x$  film layer 206 is explained. When the flow rate ratio ( $\text{CH}_2\text{F}_2$  /  $\text{C}_4\text{F}_8$ ) is 0.4 ~ 1.0, the numerical value of the selection ratio is approximately 17 or larger and when the flow rate ratio is 0.53 ~ 0.8, the selection ratio is approximately 25 or higher. Furthermore, a selection ratio of approximately 30 or higher is achieved with the flow rate ratio in a range of 0.55 ~ 0.7. When the flow rate ratio is approximately 0.57, the selection ratio is the highest at approximately 34 for the range, achieved by using the processing gas with the flow rate ratio of  $\text{C}_4\text{F}_8$ :  $\text{CH}_2\text{F}_2$ : Ar = 7: 4: 500 (sccm) corresponding to FIG. 5.

The selection ratio of the  $\text{SiO}_2$  film layer 208 relative to the  $\text{SiN}_x$  film layer 206 only needs to be approximately 20 under normal circumstances, and by adjusting the flow rates of the processing gas constituents so as to set the flow rate ratio ( $\text{CH}_2\text{F}_2$  /  $\text{C}_4\text{F}_8$ ) essentially within the range of 0.4 ~ 1.0, more desirably essentially within the range of 0.53 ~ 0.8 and even more desirably the essentially within the range of 0.55 ~ 0.7 as described earlier, a selection ratio of up to approximately 34 can be achieved. It is to be noted that in FIG. 8 the vertical axis represents the selection ratio of the  $\text{SiO}_2$  film layer relative to the  $\text{SiN}_x$  film layer 206 and the horizontal axis represents the flow rate ratio ( $\text{CH}_2\text{F}_2$  /  $\text{C}_4\text{F}_8$ ).

#### (B) Changes in pressure atmosphere inside processing chamber

Next, implementation examples achieved by varying the pressure of the atmosphere inside the processing chamber 104 are

explained. In implementation example 6 and implementation example 7 in the table below, the process etching was performed with the individual conditions other than the pressure of the atmosphere inside the processing chamber 104 set as in implementation example 3 mentioned earlier. Namely, the flow rates of the processing gas constituents were set at  $C_4F_8$ :  $CH_2F_2$ : Ar = 7: 4: 500 (sccm) as in implementation example 3. In addition, for implementation example 6 and implementation example 7, the surface uniformity of the wafer W and the selection ratio of the  $SiO_2$  film layer 208 relative to the  $SiN_x$  film layer 206 were ascertained with the resulting cross sectional shape of the wafer W illustrated in the corresponding figure, as for implementation examples 1 ~ 5 explained earlier.

Table 2

| Implementation example | Pressure atmosphere inside processing chamber (mTorr) | Wafer surface uniformity (±%) | SiO <sub>2</sub> film layer average etching rate (lambda/min) | SiO <sub>2</sub> / SiN <sub>x</sub> selection ratio | Contact hole cross sectional shape |
|------------------------|---|-------------------------------|---|---|------------------------------------|
| 6                      | 40  | 2.6                           | 3800  | 13.2  | FIG. 9                             |
| 3                      | 50  | 1.2                           | 4050  | 34.4  | FIG. 5                             |
| 7                      | 60  | 6.8                           | 4400  | 70.6  | FIG. 10                            |

While carbon does not accumulate readily at the bottoms of contact holes 210 to enable formation of contact holes 210 with a specific depth, as shown in FIG. 9, when the pressure of the atmosphere in the processing chamber 104 is set at 40 (mTorr) as in implementation example 6, the shoulder 207 of the SiN<sub>x</sub> film layer 206 becomes etched and damaged as shown in the figure. In addition, while the shoulders 207 of the SiN<sub>x</sub> film layer 206 can be protected by the carbon film in a reliable manner by setting the pressure of the atmosphere inside the processing chamber 104 at 60 (mTorr) as in implementation example 7, carbon accumulates at the bottoms of the contact holes 210 to cause an etching stop and reduce the penetration, as shown in FIG. 10.

If, on the other hand, the pressure of the atmosphere inside the processing chamber 104 is set at 50 (mTorr) as in implementation example 3 described earlier, carbon is not accumulated at the bottoms of the contact holes 210 and the shoulders 207 of the SiN<sub>x</sub> film layer 206 are not etched so that the contact holes 210 each achieving a specific shape and a specific depth are formed, as illustrated in FIG. 5.

The results discussed above indicate that by setting the pressure of the atmosphere inside the processing chamber 104 at approximately 50 (mTorr) when performing an etching process on the wafer W on the etching apparatus 100, contact holes 210 achieving a specific shape are formed at the wafer W. However, the level of the pressure of the atmosphere above is valid only in conjunction with the etching apparatus 100, and contact holes 210 may be formed differently if implementation example 3, 6 or 7 is adopted in another processing apparatus, due to a difference in the volumetric capacity of the processing chamber and the like. Accordingly, by setting the pressure atmosphere inside the processing chamber 104 in



conformance to the partial pressure corresponding to  $C_4F_8$  relative to the entire pressure of the processing gas containing  $C_4F_8$ ,  $CH_2F_2$  and Ar used in implementation example 3, which is calculated to be 0.68 (mTorr), contact holes 210 achieving a specific shape can be formed on any etching apparatus, as in implementation example 3. In addition, by setting the partial pressure as appropriate within the range of 0.4 (mTorr) ~ 0.8 (mTorr), contact holes 210 achieving a specific shape can be formed as in implementation example 3.

(C) Changes in high-frequency power applied to lower electrode

Implementation examples in which the high-frequency power applied to the lower electrode 106 is varied are explained. In the implementation examples 8 and 9 in the table below, the individual conditions other than the level of the high-frequency power applied to the lower electrode 106 were set the same as those in implementation example 3. In addition, as in implementation examples 1 ~ 7 explained earlier, the surface uniformity at the wafer W and the selection ratio of the  $SiO_2$  film layer 208 relative to the  $SiN_x$  film layer 206 were ascertained with the resulting cross sectional shape of the wafer W illustrated for implementation examples 8 and 9. It is to be noted that the frequency of the high-frequency power was set at 13.56 MHz as in implementation example 3.

Table 3

| Implementation example | High-frequency power (W) | Wafer surface uniformity (±%) | SiO <sub>2</sub> film layer average etching rate (lambda/min) | SiO <sub>2</sub> / SiN <sub>x</sub> selection ratio | Contact hole cross sectional shape |
|------------------------|--------------------------|-------------------------------|---|---|------------------------------------|
| 8                      | 1400                     | 3.6                           | 4150  | 37.7  | FIG. 11                            |
| 3                      | 1500                     | 1.2                           | 4050  | 34.4  | FIG. 5                             |
| 9                      | 1600                     | 8.9                           | 4500  | 28.9  | FIG. 12                            |

As shown in FIGS. 11 and 12, with the level of the high-frequency power applied to the lower electrode 106 at either 1400 (W) or 1600

(W) carbon accumulated less readily at the bottoms of the contact holes 210 and the shoulders 207 of the  $\text{SiN}_x$  film layer 206 did not become etched readily either. However, while the selection ratio of the  $\text{SiO}_2$  film layer 208 relative to the  $\text{SiN}_x$  film layer 206 improved when the high-frequency power was set at 1400 (W), some accumulation of carbon was observed at the bottom of the contact hole 210. No accumulation of carbon at the bottom of the contact hole 210 was observed when the high-frequency power was set at 1600 (W). It goes without saying that when high-frequency power at 1500 (W) was applied to the lower electrode 106 as in implementation example 3 described earlier, contact holes 210 achieving good a etching shape were formed, as illustrated in FIG. 5.

The results described above indicate that when performing an etching process on the wafer W by employing the etching apparatus 100 described above, contact holes 210 are formed in a specific shape at the wafer W by setting the high-frequency power applied to the lower electrode 106 within the range of 1400 (W) ~ 1600 (W). In addition, since good etching characteristics were achieved by applying high-frequency power at 1600 (W) to the lower electrode 106, it is assumed that contact holes 210 can be formed in a specific shape even when the upper limit of the level of power supplied to the lower electrode 106 is raised to 1700 (W).

It is to be noted that since the high-frequency power levels described above were set for the etching apparatus 100, contact holes 210 may not be formed as described above if implementation example 3, 8 or 9 is adopted in a different processing apparatus. Such variance of contact hole formation is attributed to the fact that the quantity of fluorine radicals entering toward the bottoms of the contact holes 210 and the quantity of carbon deposited onto the inner wall surface of the contact hole 210 are affected by the plasma density inside the

processing chamber 104. Accordingly, the density of plasma inside the processing chamber 104 was measured by applying 1400 (W) ~ 1700 (W) high-frequency power at 13.56 (MHz) to the lower electrode 106 as described earlier and the numerical values thus obtained were  $1.5 \times 10^{10}$  (number of ions /  $\text{cm}^3$ ) ~  $1.2 \times 10^{11}$  (number of ions /  $\text{cm}^3$ ). Thus, by generating plasma inside the processing chamber 104 so as to achieve a plasma density within the range of  $1.5 \times 10^{10}$  (number of ions /  $\text{cm}^3$ ) ~  $1.2 \times 10^{11}$  (number of ions /  $\text{cm}^3$ ), contact holes 210 achieving a specific shape can be formed at the wafer W.

(D) Changes in the temperature of lower the electrode mounting surface

Next, implementation examples in which the temperature of the mounting surface of the lower electrode 106 was varied are explained. In implementation examples 10 and 11 in the table below, the individual conditions other than the temperature of the mounting surface of the lower electrode 106 were set the same as those in implementation example 3. In addition, as in implementation examples 1 ~ 9 explained earlier, the surface uniformity at the wafer W and the selection ratio of the  $\text{SiO}_2$  film layer 208 relative to the  $\text{SiN}_x$  film layer 206 were ascertained with the resulting cross sectional shape of the wafer W illustrated for implementation examples 10 and 11. It is to be noted that the temperature of the inner wall surfaces of the processing chamber 104 was set at 60°C as in implementation example 3.

Table 4

| Implementation example | Lower electrode mounting surface temperature (°C) | Wafer surface uniformity (±%) | SiO <sub>2</sub> film layer average etching rate (lambda/min) | SiO <sub>2</sub> / SiN <sub>x</sub> selection ratio | Contact hole cross sectional shape |
|------------------------|---|-------------------------------|---|---|------------------------------------|
| 10                     | 20  | 6.8                           | 4400  | 20.6  | FIG. 13                            |
| 3                      | 40  | 1.2                           | 4050  | 34.4  | FIG. 5                             |
| 11                     | 60  | 3.5                           | 4250  | 58.2  | FIG. 14                            |

With the temperature of the mounting surface of the lower electrode 106 set at 20°C, contact holes 210 achieving a specific depth were

formed with the accumulation of carbon at the bottoms of the contact holes 210 occurring less readily as shown in FIG. 13, but, at the same time, the selection ratio of the  $\text{SiO}_2$  film layer 208 relative to the  $\text{SiN}_x$  film layer 206 was 20.6 and the shoulders 207 of the  $\text{SiN}_x$  film layer 206 became etched, as illustrated in the same figure. In contrast, by setting the temperature of the mounting surface of the lower electrode 106 to  $60^\circ\text{C}$ , a selection ratio of 58.2 was achieved for the  $\text{SiO}_2$  film layer 208 relative to the  $\text{SiN}_x$  film layer 206 and the shoulder 207 of the  $\text{SiN}_x$  film layer 206 were not etched as illustrated in FIG. 14. In addition, carbon did not accumulate at the bottoms of the contact holes 210 to enable formation of contact holes 210 achieving a specific depth at this temperature, as shown in the same figure. It goes without saying that when the temperature of the mounting surface of the lower electrode 106 was set at  $40^\circ\text{C}$ , as in implementation example 3, too, contact holes 210 achieving a specific depth and a specific shape were formed, as illustrated in FIG. 5.

The results discussed above indicate that by setting the temperature of the mounting surface of the lower electrode 106 as high as possible above  $20^\circ\text{C}$ , contact holes 210 achieving a specific shape can be formed at the wafer W. However, if the temperature of the wafer W rises to a level equal to or higher than a specific temperature, the photoresist film layer 212 formed over the  $\text{SiO}_2$  film layer 208 becomes melted and thus loses its function as an etching mask. For this reason, the upper limit of the temperature of the mounting surface of the lower electrode 106 should be the heat resistance temperature of the photoresist layer 212. Consequently, by setting the temperature of the mounting surface of the lower electrode 106 as appropriate within the range of  $20^\circ\text{C} \sim$  the heat resistance temperature of the photoresist layer 212, contact holes 210 achieving a specific shape can be formed at the wafer W.

(E) Comparison of implementation example 3 and the prior art

Next, implementation example 3 illustrated in FIG. 5 in which contact holes 210 achieving a specific shape were formed with the highest degree of consistency at the wafer W among implementation examples 1 ~ 11 is compared with a prior art example illustrated in FIG. 15. First, the etching conditions adopted in implementation example 3 and the prior art example are explained. In both implementation example 3 and the prior art example, an etching process was implemented by using the etching apparatus 100, with the temperatures of the upper electrode 122 and the internal wall surfaces of the processing chamber 104 sustained at 60 °C and the temperature of the mounting surface of the lower electrode 110 sustained at 40°C. In addition, high-frequency power at 1500W with a frequency of 13.56 (MHz) was applied to the lower electrode 106. Wafers W with a 200 mm diameter were used.

In addition, while the processing gas with its gas composition and flow rate ratio expressed as  $C_4F_8$ :  $CH_2F_2$ : Ar = 7: 4: 500 (sccm) was induced into the processing chamber 104 in implementation example 3 as described earlier, a processing gas with its gas composition and flow rate ratio expressed as  $C_4F_8$ : CO: Ar = 18:300:380 (sccm) was induced into the processing chamber 104 in the prior art example. In addition, while the pressure of the atmosphere inside the processing chamber 104 was set at 50 (mTorr) as described above in implementation example 3, the pressure of the atmosphere inside the processing chamber 104 was set at 40 (mTorr) in the prior art example.

Next, the etching rates of the  $SiO_2$  film layer 208, the degrees of surface uniformity at the wafer W and the selection ratios of the  $SiO_2$  film layer 208 relative to the  $SiN_x$  film layer 206 achieved in implementation example 3 and the prior art example are explained.

First, the etching rates of the SiO<sub>2</sub> film layer 208 are explained. In implementation example 3, an etching rate of 4000 (Å / min) was achieved at the center of the wafer W and an etching rate of 4100 (Å / min) was achieved at the edge, as explained earlier. In the prior art example, on the other hand, an etching rate of 4600 (Å / min) was achieved at the center and an etching rate of 5200 (Å / min) was achieved at the edge. In addition, while the degree of surface uniformity at the wafer W achieved in implementation example 3 was  $\pm 1.2\%$  as explained earlier, the corresponding degree achieved in the prior art example was  $\pm 6.1\%$ . Furthermore, while a selection ratio of 34.4 was achieved in implementation example 3 for the SiO<sub>2</sub> film layer 208 relative to the SiN<sub>x</sub> film layer 206, the corresponding ratio achieved in the prior art example was 11.2.

The results discussed above indicate that while the etching rate of the SiO<sub>2</sub> film layer 208 is lower than that achieved in the prior art example, improvements are achieved in the surface uniformity of the wafer W and the selection ratio of the SiO<sub>2</sub> film layer 208 relative to the SiN<sub>x</sub> film layer 206 when the wafer W is processed through the etching process adopted in implementation example 3, over those achieved in the prior art example. A particularly pronounced improvement was observed in implementation example 3 over the prior art example with regard to the selection ratio of the SiO<sub>2</sub> film layer 208 relative to the SiN<sub>x</sub> film layer 206, as shown in FIG. 15. Namely, the shoulders 207 of the SiN<sub>x</sub> film layer 206 exposed inside the contact hole 210 did not become etched at the wafer W shown in FIG. 5 having undergone the process adopted in implementation example 3 to enable formation of contact holes 210 achieving a specific shape. In contrast, at the wafer W shown in FIG. 15 having undergone the etching process in the prior art example, the SiO<sub>2</sub> film layer 204 covering the gates 202 became etched and ultimately



damaged, as well as the shoulder 207 of the  $\text{SiN}_x$  film layer 206. This leads to the conclusion that the contact holes 210 achieving a specific shape can be formed at the wafer W with a greater degree of ease by using the processing gas constituted of the mixed gas containing  $\text{C}_4\text{F}_8$ ,  $\text{CH}_2\text{F}_2$  and Ar in the implementation example rather than processing the wafer W with the processing gas constituted of the mixed gas containing  $\text{C}_4\text{F}_8$ , CO and Ar utilized in the prior art.

While the invention has been particularly shown and described with respect to a preferred embodiment and specific implementation examples thereof by referring to the attached drawings, the present invention is not limited to these examples and it will be understood by those skilled in the art that various changes in form and detail may be made therein without departing from the spirit, scope and teaching of the invention.

For instance, while an explanation is given above in reference to the embodiment on an example in which the mixed gas containing  $\text{C}_4\text{F}_8$ ,  $\text{CH}_2\text{F}_2$  and Ar alone is used as the processing gas to form contact holes, the present invention is not limited to such an example.

For instance, when forming contact holes 210 at the wafer W by employing the etching apparatus 100, for instance, the mixed gas with its gas composition and flow rate ratio expressed as  $\text{C}_4\text{F}_8$ : CO: Ar = 18:300:380 (sccm) explained in reference to the prior art example may be first used as a processing gas to process the wafer W. At this time, the pressure of the atmosphere inside the processing chamber 104 shown in FIG. 1, should be set at approximately 55 (mTorr). Then, before or after the shoulder 207 of the  $\text{SiN}_x$  film layer 206 become exposed inside the contact holes 210, a switch may be made to another mixed gas with its gas composition and flow rate ratio expressed as  $\text{C}_4\text{F}_8$ :  $\text{CH}_2\text{F}_2$ : Ar = 7:4:500 (sccm) as in implementation example 3 to process the wafer W. The pressure of the atmosphere

inside the processing chamber 104 during this process should be set at approximately 50 (mTorr).

By utilizing the mixed gas containing  $C_4F_8$ , CO and Ar as a processing gas in this manner, a carbon film can be deposited at the inner wall surface of the contact holes 210 with a high degree of reliability so that the contact holes 210 are formed in a specific shape while preventing the inner wall surfaces from becoming etched. In addition, by switching to another mixed gas containing  $C_4F_8$ ,  $CH_2F_2$  and Ar before or after the shoulder 207 of the  $SiN_x$  film layer 206 become exposed, fluorine radicals can be allowed into the contact holes 210 to reach their bottoms in a reliable manner, to prevent a reduction in the penetration attributable to accumulation of carbon at the bottoms and prevent occurrence of an etching stop. Furthermore, since the shoulder 207 of the  $SiN_x$  film layer 206 exposed inside the contact holes 210 are protected by the carbon film, the shoulder 207 do not become etched to enable quick formation of contact holes 210 achieving a higher aspect ratio and a specific shape. It is to be noted that a switch to the mixed gas containing  $C_4F_8$ ,  $CH_2F_2$  and Ar may be effected either before or after the shoulder 207 of the  $SiN_x$  film layer 206 become exposed as explained earlier, or may be effected concurrently as the shoulder 207 of the  $SiN_x$  film layer 206 become exposed. In addition, the switch to the other processing gas may be effected by, for instance, using a preset time point as reference, or may be effected in conformance to the end point detection value ascertained based upon the emission spectrum of the plasma inside the processing chamber 104.

It is to be noted that the process conditions other than the processing gas compositions, the flow rates of the processing gas constituents and the atmospheric pressure inside the processing chamber 104 adopted in the individual etching methods are set

essentially the same as those adopted in the embodiment described earlier. In addition, while an explanation is given above in reference to the individual etching methods on an example in which Ar is added into the processing gas, the present invention is not restricted by such particulars, and any of various types of gases including an inert gas such as Kr and gases such as  $O_2$ ,  $N_2$ , CO or  $CO_2$  may be added in the processing gas. Furthermore, instead of Ar, any of various inert gases may be added, or the present invention may be implemented without adding any inert gas.

In addition, while an explanation is given in reference to the embodiment on an example in which the etching apparatus is provided with a magnet, the present invention is not limited to this structural example, and it may be adopted in a plasma-etching apparatus not having such a magnet. Moreover, while an explanation is given above on an etching apparatus in which high-frequency power is supplied to the lower electrode alone, the present invention is not restricted by such structural details, and it may be implemented by using a plasma-etching apparatus in which high-frequency power is applied to both the upper electrode and the lower electrode or a plasma-etching apparatus in which high-frequency power is applied to the upper electrode alone.

According to the present invention, in which a gas containing at least  $C_4F_8$  and  $CH_2F_2$  is utilized as the processing gas, etching ions can be allowed into contact holes toward their bottoms in a reliable manner while forming a carbon film at the inner wall surface of the contact holes and, more specifically, at the shoulder of the  $SiN_x$  layer exposed inside the contact holes, to prevent accumulation of carbon at the bottoms. As a result, since the shoulder of the  $SiN_x$  film layer that tend to become etched particularly readily can be protected, damage to the gates or to the insulating film layer covering the gates

is prevented to achieve an improvement in yield. In addition, since the bottoms of the contact holes can be etched with a high degree of reliability without reducing the penetration or causing an etching stop, contact holes achieving a high aspect ratio are formed with ease.

### **INDUSTRIAL APPLICABILITY**

The present invention may be adopted in an etching method employed in a semiconductor manufacturing process, and in particular, may be adopted in an etching method for plasma-etching an  $\text{SiO}_2$  film layer covering an  $\text{SiN}_x$  film layer formed at a workpiece placed inside an air-tight processing chamber by raising to plasma a processing gas induced into the processing chamber.

**What is claimed is;**

1. An etching method for plasma-etching an  $\text{SiO}_2$  film layer covering an  $\text{SiN}_x$  film layer formed at a workpiece placed inside an air-tight processing chamber by raising to plasma a processing gas induced into said processing chamber, wherein;

said processing gas is a mixed gas containing at least  $\text{C}_4\text{F}_8$  and  $\text{CH}_2\text{F}_2$ .

2. An etching method for plasma-etching an  $\text{SiO}_2$  film layer covering an  $\text{SiN}_x$  film layer formed at a workpiece placed inside an air-tight processing chamber by raising to plasma a processing gas induced into said processing chamber, comprising;

a first step in which said  $\text{SiO}_2$  film layer is etched by using a mixed gas containing at least  $\text{C}_4\text{F}_8$  and CO as said processing gas; and

a second step in which a switch is made to a mixed gas containing at least  $\text{C}_4\text{F}_8$  and  $\text{CH}_2\text{F}_2$  to be used as said processing gas to etch said  $\text{SiO}_2$  film layer immediately before said  $\text{SiN}_x$  film layer becomes exposed.

3. An etching method for plasma-etching an  $\text{SiO}_2$  film layer covering an  $\text{SiN}_x$  film layer formed at a workpiece placed inside an air-tight processing chamber by raising to plasma a processing gas induced into said processing chamber, comprising;

a first step in which said  $\text{SiO}_2$  film layer is etched by using a mixed gas containing at least  $\text{C}_4\text{F}_8$  and CO as said processing gas; and

a second step in which a switch is made to a mixed gas containing at least  $\text{C}_4\text{F}_8$  and  $\text{CH}_2\text{F}_2$  to be used as said processing gas to etch said  $\text{SiO}_2$  film layer immediately after said  $\text{SiN}_x$  film layer becomes exposed.

4. An etching method according to any of claims 1, 2 and 3, wherein;

the flow rate ratio ( $\text{CH}_2\text{F}_2 / \text{C}_4\text{F}_8$ ) of  $\text{C}_4\text{F}_8$  and  $\text{CH}_2\text{F}_2$  in said mixed gas containing at least  $\text{C}_4\text{F}_8$  and  $\text{CH}_2\text{F}_2$  is set essentially within a range of 0.4 ~ 1.0.

5. An etching method according to any of claims 1, 2 and 3, wherein;

the partial pressure corresponding to  $\text{C}_4\text{F}_8$  relative to the entire pressure of said mixed gas containing at least  $\text{C}_4\text{F}_8$  and  $\text{CH}_2\text{F}_2$  is set essentially within a range of 0.4 (mTorr) ~ 0.8 (mTorr).

6. An etching method according to any of claims 1, 2 and 3, wherein;

the density of plasma excited inside said processing chamber is set essentially within a range of  $1.5 \times 10^{10}$  (number of ions /  $\text{cm}^3$ ) ~  $1.2 \times 10^{11}$  (number of ions /  $\text{cm}^3$ ).

7. An etching method according to any of claims 1, 2 and 3, wherein;

said workpiece is placed on a mounting surface of a susceptor provided inside said processing chamber; and

the temperature of said susceptor is set essentially within a range of 20 °C ~ the heat resistance temperature of a photoresist layer constituting a mask pattern for said  $\text{SiO}_2$  film layer.

8. An etching method according to any of claims 1, 2 and 3, wherein;

said mixed gas containing at least  $\text{C}_4\text{F}_8$  and  $\text{CH}_2\text{F}_2$  further contains an inert gas.

9. An etching method according to claim 2 or 3, wherein;  
said mixed gas containing at least  $C_4F_8$  and CO further contains an inert gas.

### **Abstract of the Disclosure**


A lower electrode 106 with the temperature at its mounting surface set at 40°C is provided inside a processing chamber 104 of an etching apparatus 100. After a wafer W is placed on the lower electrode 106, a processing gas with its gas composition and gas flow rate expressed as  $C_4F_8:CH_2F_2:Ar = 7:4:500$  (sccm) is induced into the processing chamber 104 while sustaining the pressure of the atmosphere inside the processing chamber 104 at 50 (mTorr). High-frequency power at 1500 (W) with the frequency at 13.56 (MHz) is applied to the lower electrode 106 to generate plasma. With the plasma thus generated, a carbon film is formed at shoulder 207 of an  $SiN_x$  film layer 206 exposed inside a contact hole 210 and, at the same time, accumulation of carbon at the bottom of the contact hole 210 is prevented, to form a contact hole 210 achieving a high aspect ratio while preventing damage to the  $SiN_x$  film layer.



## Key

|               |                               |
|---------------|-------------------------------|
| 100           | etching apparatus             |
| 104           | processing chamber            |
| 106           | lower electrode               |
| 116           | temperature control mechanism |
| 120           | high-frequency source         |
| 122           | upper electrode               |
| 122a          | gas outlet hole               |
| 134, 140, 146 | flow-regulating valve         |
| 136, 142, 148 | gas supply source             |
| 200           | Si substrate                  |
| 202           | gate                          |
| 204           | insulating film layer         |
| 206           | SiN <sub>x</sub> film layer   |
| 207           | shoulder                      |
| 208           | SiO <sub>2</sub> film layer   |
| 210           | contact hole                  |
| W             | wafer                         |

FIG.1



2 / 9

FIG.2





FIG.3



Implementation Example 1

FIG.4




FIG.5






FIG.6



Implementation Example 4

FIG.7



Implementation Example 5

FIG.8






FIG.9




Implementation Example 6

FIG.10




Implementation Example 7

FIG.11



Implementation Example 8


FIG.12



Implementation Example 9




FIG.13



Implementation Example 10


FIG.14




Implementation Example 11

FIG.15

Center



Edge



Example of Prior Art

## DECLARATION AND POWER OF ATTORNEY

As a below named inventor, I hereby declare that: my residence, post office address and citizenship are as stated below next to my name; I believe I am the original, first, and sole inventor (if only one name is listed below) or an original, first, and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled: ETCHING METHOD

and/or ~~was~~ filed on November 20, 2000 as United States Application Serial No. 09/700,785 the specification of which ~~is~~ <sup>is</sup> attached No. PCT/JP99/02578 and was amended on March 9, 2000 (if applicable). or PCT International Application

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above. I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR § 1.56.

I hereby claim foreign priority benefits under 35 U.S.C. § 119(a)-(d) or § 365(b) of any foreign application(s) for patent or inventor's certificate or § 365(a) of any PCT international application(s) designating at least one country other than the United States, listed below and have also identified below, any foreign application(s) for patent or inventor's certificate, or any PCT International application(s) having a filing date before that of the application(s) of which priority is claimed:

| Country | Application Number | Date of Filing | Priority Claimed Under 35 U.S.C.                                    |
|---------|--------------------|----------------|---|
| Japan   | JP10-158436        | May 22, 1998   | <input checked="" type="checkbox"/> YES <input type="checkbox"/> NO |
| PCT     | PCT/JP99/02578     | May 18, 1999   | <input checked="" type="checkbox"/> YES <input type="checkbox"/> NO |

I hereby claim the benefit under 35 U.S.C. § 119(e) of any United States provisional application(s) listed below:

| Application Number | Date of Filing |
|--------------------|----------------|
|                    |                |
|                    |                |

I hereby claim the benefit under 35 U.S.C. § 120 of any United States application(s) or § 365(c) of any PCT International application(s) designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application(s) in the manner provided by the first paragraph of 35 U.S.C. § 112, I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR § 1.56 which became available between the filing date of the prior application(s) and the national or PCT International filing date of this application:

| Application Number | Date of Filing | Status (Patented, Pending, Abandoned) |
|--------------------|----------------|---------------------------------------|
|                    |                |                                       |

I hereby appoint the following attorney and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith. FINNEGAN, HENDERSON, FARABOW, GARRETT & DUNNER, L.L.P., Douglas B. Henderson, Reg. No. 20,291; Ford F. Farabow, Jr., Reg. No. 20,630; Arthur S. Garrett, Reg. No. 20,338; Donald R. Dunner, Reg. No. 19,073; Brian G. Brunsvold, Reg. No. 22,593; Tipton D. Jennings, IV, Reg. No. 20,645; Jerry D. Voight, Reg. No. 23,020; Laurence R. Heftner, Reg. No. 20,827; Kenneth E. Payne, Reg. No. 23,098; Herbert H. Mintz, Reg. No. 26,691; C. Larry O'Rourke, Reg. No. 26,014; Albert J. Santorelli, Reg. No. 22,610; Michael C. Elmer, Reg. No. 25,857; Richard H. Smith, Reg. No. 20,609; Stephen L. Peterson, Reg. No. 26,325; John M. Romary, Reg. No. 26,331; Bruce C. Zotter, Reg. No. 27,680; Dennis P. O'Reilley, Reg. No. 27,932; Allen M. Sokal, Reg. No. 26,695; Robert D. Bajefsky, Reg. No. 25,387; Richard L. Stroup, Reg. No. 28,478; David W. Hill, Reg. No. 28,220; Thomas L. Irving, Reg. No. 28,619; Charles E. Lipsey, Reg. No. 28,165; Thomas W. Winland, Reg. No. 27,605; Basil J. Lewis, Reg. No. 28,818; Martin I. Fuchs, Reg. No. 28,508; E. Robert Yoches, Reg. No. 30,120; Barry W. Graham, Reg. No. 29,924; Susan Haberman Griffen, Reg. No. 30,907; Richard B. Racine, Reg. No. 30,415; Thomas H. Jenkins, Reg. No. 30,857; Robert E. Converse, Jr., Reg. No. 27,432; Clair X. Mullen, Jr., Reg. No. 20,348; Christopher P. Foley, Reg. No. 31,354; John C. Paul, Reg. No. 30,413; Roger D. Taylor, Reg. No. 28,992; David M. Kelly, Reg. No. 30,953; Kenneth J. Meyers, Reg. No. 25,146; Carol P. Einaudi, Reg. No. 32,220; Walter Y. Boyd, Jr., Reg. No. 31,738; Steven M. Anzalone, Reg. No. 32,025; Jean B. Fordis, Reg. No. 32,984; Barbara C. McCurdy, Reg. No. 32,120; James K. Hammond, Reg. No. 31,964; Richard V. Burgujian, Reg. No. 31,744; J. Michael Jakes, Reg. No. 32,824; Thomas W. Banks, Reg. No. 32,719; Christopher P. Isaac, Reg. No. 32,616; Bryan C. Diner, Reg. No. 32,409; M. Paul Barker, Reg. No. 32,013; Andrew Chanho Sonu, Reg. No. 33,457; David S. Forman, Reg. No. 33,694; Vincent P. Kovalick, Reg. No. 32,867; James W. Edmondson, Reg. No. 33,871; Michael R. McGurk, Reg. No. 32,045; Joann M. Neth, Reg. No. 36,363; Gerson S. Panitch, Reg. No. 33,751; Cheri M. Taylor, Reg. No. 33,216; Charles E. Van Horn, Reg. No. 40,266; Linda A. Wadler, Reg. No. 33,218; Jeffrey A. Berkowitz, Reg. No. 36,743; Michael R. Kelly, Reg. No. 33,921; James B. Monroe, Reg. No. 33,971; Doris Johnson Hines, Reg. No. 34,629; Allen R. Jensen, Reg. No. 28,224; Lori Ann Johnson, Reg. No. 34,498; and David A. Manspeizer, Reg. No. 37,540 and \_\_\_\_\_ Please address all correspondence to FINNEGAN, HENDERSON, FARABOW, GARRETT & DUNNER, L.L.P., 1300 I Street, N.W., Washington, D.C. 20005, Telephone No. (202) 408-4000.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

|  |  |                                  |
|--|--|----------------------------------|
| Full Name of First Inventor<br><u>Yobun ITO</u>  | Inventor's Signature<br><u>yobun ITO</u> | Date<br><u>November 13, 2000</u> |
| Residence<br><u>Ishizakakopo 410, 2-54-1, Shimoishihara, Chofu-shi, Tokyo 182-0034 Japan</u>           | Citizenship<br><u>Japanese</u>           |                                  |
| Post Office Address<br><u>Ishizakakopo 410, 2-54-1, Shimoishihara, Chofu-shi, Tokyo 182-0034 Japan</u> | <u>JPX</u>                               |                                  |

|   |  |  |                           |
|---|--|--|---------------------------|
| Full Name of Second Inventor<br>Masahiro YAMADA   |  | Inventor's Signature<br><i>Masahiro Yamada</i>   | Date<br>November 20, 2000 |
| Residence<br>Iguruhausu 202, 6-7-10, Nakanoshima, Tama-ku,<br>Kawasaki-shi, Kanagawa 214-0012 Japan           |  | JPX  | Citizenship<br>Japanese   |
| Post Office Address<br>Iguruhausu 202, 6-7-10, Nakanoshima, Tama-ku, Kawasaki-shi,<br>Kanagawa 214-0012 Japan |  |  |                           |
| Full Name of Third Inventor<br>Kouichiro INAZAWA  |  | Inventor's Signature<br><i>Kouichiro Inazawa</i> | Date<br>November 13, 2000 |
| Residence<br>5-33-7-505, Funabashi, Setagaya-ku, Tokyo 156-0055 Japan   |  | JPX  | Citizenship<br>Japanese   |
| Post Office Address<br>5-33-7-505, Funabashi, Setagaya-ku, Tokyo 156-0055 Japan                               |  |  |                           |
| Full Name of Fourth Inventor  |  | Inventor's Signature                             | Date                      |
| Residence   |  |  | Citizenship               |
| Post Office Address   |  |  |                           |
| Full Name of Fifth Inventor   |  | Inventor's Signature                             | Date                      |
| Residence   |  |  | Citizenship               |
| Post Office Address   |  |  |                           |
| Full Name of Sixth Inventor   |  | Inventor's Signature                             | Date                      |
| Residence   |  |  | Citizenship               |
| Post Office Address   |  |  |                           |
| Full Name of Seventh Inventor   |  | Inventor's Signature                             | Date                      |
| Residence   |  |  | Citizenship               |
| Post Office Address   |  |  |                           |
| Full Name of Eighth Inventor  |  | Inventor's Signature                             | Date                      |
| Residence   |  |  | Citizenship               |
| Post Office Address   |  |  |                           |
| Full Name of Ninth Inventor   |  | Inventor's Signature                             | Date                      |
| Residence   |  |  | Citizenship               |
| Post Office Address   |  |  |                           |